P: 800-955-9649

Email: <u>sales@barbourplastics.com</u>
Web: <u>www.barbourplastics.com</u>

## **Rigid Vinyl Compound (COMPBL)**

COMPBL is a rigid PVC with excellent impact strength and a higher density than a standard rigid PVC. This compound is designed for applications requiring the following properties:

- Good Weatherability
  - Gloss

• Impact Strength

- Toughness
- Flame Retardant
- UL and NSF 50/61 Listed

Some uses include: Fence Cap, Pipe, Medical, and Food contact.

Typical Properties	Nominal Value	ASTM Test Method
Specific Gravity	1.47	D-792
1/8" Izod Impact, ft/lbs in notch	15.0	D-256
Tensile Yield Strength, 10³ psi	6.5	D-638
Tensile Modulus, 10⁵ psi	3.8	D-638
Flexural Yield Strength, 10 <sup>3</sup> psi	12.1	D-790
Flexural Modulus, 10⁵ psi	4.0	D-790
DTUL @264 psi, °C	72.2	D-648
Coefficient of Linear Thermal Expansion	4.0x10 <sup>-5</sup> in/in °F	D-696
Flame Class	V-0 @ 0.72mm	UL-94