P: 800-955-9649

Email: sales@barbourplastics.com Web: www.barbourplastics.com

## **Acrylonitrile Butadiene Styrene-ABS(COMPXA)**

COMPXA is a RoHS compliant ABS. It has UL Yellow Cards E560070-656073 and E56070-101317482. This compound is designed for applications requiring the following properties:

- Good Impact Resistance Flame Retardant
- Good dimensional stability

- Excellent Appearance
- Poor Chemical Resistance
- Good Toughness

Some uses include: Automotive interior trim, Medical, Computer, and Edge Trims.

Typical Properties	Nominal Value	ASTM Test Method
Specific Gravity	1.19	D-792
Hardness (R-scale)	100	D-785
1/8" Izod Impact, ft/lbs in notch	4.0	D-256
Tensile Strength, 10³ psi Break	4.93	ISO 527-2/50
Flexural Strength, 10 <sup>3</sup> psi	8.82	D-790
Flexural Modulus, 10⁵ psi	2.99	D-790
DTUL @264 psi, °C unannealed	73.0	D-648
Flame Class (1.5mm)	VO	UL-94